

BAS Zink

RM	194e
Best.Nr.	Zi-06001
Fe	0,001
Pb	0,002
Zn	99,99

BRAMMER Zink

RM	SP5
Best. Nr.	Zi-07001
Pb	0,0003
Al	0,005
Fe	0,001
Sb	<0,0005
Cu	0,0004
Cd	<0,0005
Sn	0,0010
Mg	<0,0005
Zn	rest